






DESCRIPTION			
Total thickness	EN ISO 24346 (EN 428)	mm	2.00
Weight	EN ISO 23997 (EN 430)	g/sq.m	3060
Width of sheet	EN ISO 24341 (EN 426)	cm	200
Length of sheet	EN ISO 24341 (EN 426)	lm	20
CLASSIFICATION			
Standard / Product specification		-	EN ISO 10581 (EN 649)
European classification	EN ISO 10874 (EN 685)	class	34 - 43
Fire rating	EN 13501-1	class	B _n -s1
Electrical resistance *	EN 1081	Ohm	$10^4 \leq R_t \leq 10^6$
	IEC 61340-4-1	Ohm	$\leq 10^9$
	IEC 61340-4-5	Ohm	$\leq 10^9$
	ANSI / ESD-STM 7.1	Ohm	$\leq 10^9$
Static electrical propensity	EN 1815	kV	< 2
	IEC 61340-4-5	V	$\leq 100^{**}$
Protection against electrostatic discharges	ESD 20.20	-	OK
	IEC 61340-5-1	-	OK
Slip resistance	DIN 51130	class	R9
PERFORMANCE			
Wear resistance	EN 660.2	mm ³	≤ 4.0
Wear group	NF 189	group	P
Type Binder content	ISO 10581	type	I
Dimensional stability	EN ISO 23997 (EN 434)	%	$\leq 0,40$
Residual indentation	EN ISO 24343-1 (EN 433)	mm	$\sim 0,02$
Castor chair test (type W)	ISO 4918 (EN 425)	-	OK
Thermal conductivity	EN ISO 10456 (EN 12 524)	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Surface treatment	-	-	Evercare™
Chemical products resistance	EN ISO 26987 (EN 423)	-	OK
ENVIRONMENT / INDOOR AIR QUALITY			
TVOC after 28 days	ISO 16000-6	µg/ m ³	< 10
Certification	-	-	Floorscore®
MARQUAGE CE			
	EN 14041	-	  
		-	

* Measured before installation

** Measured with ESD shoes (ABEBA and Uvex)

Important : please refer to GERFLOR installation guidelines – www.gerflor.com